

Hose type: **202AA063760000**

ID x OD: **63 x 76**

Lot: **46821**

Order confirmation: ----

Brand: **ALFAGOMMA - ITALY - 202 (EVOLUTION logo) 10 bar (150 psi) GENERAL PURPOSE - EPDM Ω/T**

Manufacturing date: **25/2/2023**

Test date: **25/2/2023**

Test code: **DHM230225/09**

Subject: **Shanghai Fengjun Fluid Technology Co,LTD**

Property	Norm	Chapter	Test metod	Limits		Results
				Min	Max	
Inside diameter	Specifica Alfagomma	01	NI EN ISO 467	61.8	64.2	63.6 mm
Thickness	Specifica Alfagomma	02	NI EN ISO 467	5	7	6.7 mm
Minimum tube thickness	Specifica Alfagomma	03	NI EN ISO 467			2.3 mm
Minimum cover thickness	Specifica Alfagomma	04	NI EN ISO 467			1.7 mm
Outside diameter	Specifica Alfagomma	05	NI EN ISO 467	74.4	77.6	76.9 mm
Change in length at working pressure	Specifica Alfagomma	06	NI EN ISO 140			6.6 % 10 bar
Change in outside diameter at working pressu	Specifica Alfagomma	07	NI EN ISO 140			0.3 % 10 bar
Twist at working pressure	Specifica Alfagomma	08	NI EN ISO 140			4.1 °/m 10 bar
Change in length at proof pressure	Specifica Alfagomma	09	NI EN ISO 140			13.1 % 15 bar
Change in outside diameter at proof pressure	Specifica Alfagomma	10	NI EN ISO 140			1.5 % 15 bar
Twist at proof pressure	Specifica Alfagomma	11	NI EN ISO 140			4.4 °/m 15 bar
Burst pressure	Specifica Alfagomma	12	EN ISO 1402	30		43 bar
Adhesion (Filler/Cover)	Specifica Alfagomma	13	UNI EN 8033	1.5		3 N/mm
Adhesion (Lining/Filler)	Specifica Alfagomma	13	UNI EN 8033	1.5		3.4 N/mm
Weight hose	Specifica Alfagomma	44	Interno	2.009		2.192 kg/m
Electrical resistance tube	TRbF 131/2	5.7.1	RbF DIN 5348f	1		0.012 MOhm
Electrical resistance cover/cover	TRbF 131/2	8	RbF 131/2 5.7.	1		0.009 MOhm

Conclusions:

This test is passed

上海洋峻流体科技有限公司 - AG授权分销商

TEL:+86-21-58400374/58400394

FAX:+86-21-50182690

E-mail:fengjunfluid@163.com

ADD:上海市奉贤区浦卫公路6655号一号厂房

<https://tiger-flex.com.cn/>

Pagina 1 di 1

Laboratory operator : 

Laboratory Mgr : 